

	<i>used zirconia powder</i>	<i>time / s</i>						
		<i>1000</i>	<i>2000</i>	<i>3000</i>	<i>4000</i>	<i>5000</i>	<i>6000</i>	<i>7000</i>
<i>dynamic viscosity / Pa·s</i>	TZ-E	36.8	36.7	36.8	36.7	36.8	36.6	36.8
	TZ-B	13.4	12.0	11.2	10.7	10.2	9.95	9.84
	ZP-AW	13.0	12.6	12.3	12.1	12.0	11.9	11.9
	ZP-B	6.5	6.2	6.0	5.8	5.6	5.4	5.2